



Technical data sheet

Rev. 10/2025

NBR 75 ShA BLK

Acrylnitrile-butadiene-rubber, black

| Properties | Value | Unit | DIN Standard |
|--------------------------|-------|-------------------|-------------------|
| Hardness | 75±5 | Shore A | DIN ISO 7619-1 |
| Density | 1,21 | g/cm ³ | DIN EN ISO 1183-1 |
| 100% Modulus | 5,8 | Mpa | DIN 53504 |
| Elongation at break | 217 | % | DIN 53504 |
| Tensile strength | 13,9 | Mpa | DIN 53504 |
| Compression set 23°C/70h | 3,2 | % | DIN ISO 815-1 |
| Compression set 70°C/22h | 5,9 | % | DIN ISO 815-1 |
| Rebound resilience | 30 | % | DIN ISO 4662:2017 |
| Tear strength | 4,7 | kN/m | DIN ISO 34-1 A |
| Abrasion resistance | 135 | mm ³ | DIN ISO 4649 B |
| Min. Service temperature | -30 | °C | |
| Max. Service temperature | +95 | °C | |

Advantages and stability:

- **NBR 75ShA compound in a softer formulation**, designed for general-purpose sealing applications where flexibility and reliable performance are required.
- **Good resistance** to mineral oils, HFC fluids, and cold water, ensuring stable operation and long service life under typical industrial conditions.
- **Versatile in use** – suitable for rod and piston seals, wiper seals, and rotary sealing elements.

All data provided above are based on random samples taken from our ongoing production. The results were determined using standard test specimens in accordance with ISO, DIN, and ASTM methods. These results cannot be directly applied to specific finished components.

Any technical information or advice we provide—whether verbal, written, or based on testing—is given to the best of our knowledge. Nevertheless, this information should be regarded as non-binding guidance and does not release the user from the obligation to verify the suitability of our products for their intended process or application. Possible third-party property rights must also be observed.

Since the use, application, and processing of our products take place beyond our control, they remain solely the responsibility of the user. In any case where liability may arise, it shall be limited to damages not exceeding the value of the product supplied and used.

We do, however, guarantee the flawless quality of our products in accordance with our general terms and conditions of sale and delivery.

